

**Characterization Of Tungstophosphoric Acid Supported On
MCM-41
Mesoporous Silica Using N-Hexane Cracking, Benzene
Adsorption, And
X-Ray Diffraction**

**Jalil, PA; Al-Daous, MA; Al-Arfaj, ARA; Al-Amer, AM; Beltramini, J; Barri,
SAI**

ELSEVIER SCIENCE BV, APPLIED CATALYSIS A-GENERAL; pp: 159-171; Vol: 207

King Fahd University of Petroleum & Minerals

<http://www.kfupm.edu.sa>

Summary

MCM-41 with all-silica composition was synthesized with unit cell parameters $a=b=60$ Angstrom. The material was characterized by X-ray powder diffraction and benzene adsorption. Combinations of unit cell parameter, benzene adsorption and crystal density determination have given values for the pore diameter and wall thickness in the ab -plane of the unit cell. The unit cell size shrank upon impregnation of the material with tungstophosphoric acid, The catalytic activity of tungstophosphoric acid (HPW) supported on the all-silica mesoporous MCM-41 material has been evaluated for the cracking of n-hexane, The catalyst showed a very high activity of n-hexane cracking at a temperature as low as 200 degreesC, at very low space velocity. However, the catalyst deactivated rapidly due to coke deposition on the acid sites. At higher temperature the activity declined, most likely because of the heteropoly-acid thermal instability. Both X-ray powder diffraction and infra-red spectroscopy have shown evidence for the heteropoly-acid instability starting at 300 degreesC. The type of the solvent used in the impregnation affected the dispersion of HPW on the MCM-41 material as indicated by benzene adsorption measurement, but it did not influence the catalytic performance for n-hexane cracking. In the case of aqueous solution, the benzene adsorption was lower than that of the parent MCM-41

material. The reduced adsorption capacity was probably due to the presence of the HPW at the pore mouth of the cylindrical channels, causing narrowing and blocking of some sections of the channels. Moreover, the adsorption isotherm showed a micropore characteristic supporting the pore narrowing proposal. In the case of using methanol solvent for the impregnation, the full adsorption capacity was retained, indicating a much higher dispersion of the HPW throughout the channels of the MCM-41 material. The benzene adsorption isotherm also showed the characteristic of mesoporosity and the adsorption capacity was not appreciably reduced. Characterization of the spent catalyst after n-hexane cracking test showed additional reduction in the benzene adsorption capacity for the aqueous impregnated catalyst. Again the methanol-impregnated catalyst had almost a full adsorption capacity. (C) 2001 Elsevier Science B.V. All rights reserved.

References:

1. BLASCO T, 1998, J CATAL, V177, P306
2. BRUNAUER S, 1940, J AM CHEM SOC, V62, P1723
3. COUSTEL N, 1994, J CHEM SOC CHEM COMM, P967
4. DIAS JA, 1999, J CATAL, V183, P83
5. IZUMI Y, 1989, B CHEM SOC JPN, V62, P2159
6. IZUMI Y, 1992, ZEOLITE CLAY HETEROP
7. KOZHEVNIKOV IV, 1995, CATAL REV SCI ENG, V37, P311
8. KOZHEVNIKOV IV, 1996, J MOL CATAL A-CHEM, V114, P287
9. LUCAS HJ, 1934, J AM CHEM SOC, V56, P460
10. MISONO M, 1987, CATAL REV, V29, P269
11. MIZUNO N, 1994, J MOL CATAL, V86, P319
12. NOWINSKA K, 1990, J CHEM SOC CHEM 0101, P44
13. NOWINSKA K, 1991, J CHEM SOC FARADAY T, V87, P749
14. OULMEKKI A, 1992, REACT KINET CATAL L, V48, P593
15. OULMEKKI A, 1992, REACT KINET CATAL L, V48, P601
16. OULMEKKI A, 1992, REACT KINET CATAL L, V48, P607
17. TSIGDINOS GA, 1970, INORG CHEM, V9, P2488
18. WELLS AF, 1962, STRUCTURAL INORGANIC

For pre-prints please write to: abstracts@kfupm.edu.sa